



**CHARACTERISTICS**

- Universal MS hybrid polymer based adhesive sealant
- Jointing and gluing
- Bonds also with slightly moist supports
- Suitable for use with natural stone
- Does not cause any corrosion in metal joints
- Paintable with most water and solvent based paints
- Extremely strong and permanently elastic
- Excellent U.V., weather and aging resistance
- Solvent, isocyanate and phthalate free

**APPLICATIONS**

- For interior and exterior use.
- All jointing where flexibility is important:
  - Sealing of horizontal and vertical expansion and connecting joints (max. width 50mm).
  - Sealing of joints and cracks in car, caravan, train and bus construction, in containers, in air-conditioning installations...
  - Sealing between frame and wall, connecting joints of window and door frames, in facades and shop fronts...
  - Sealing and gluing work in veranda's, bathrooms, kitchens, etc.
  - Sound proofing between concrete and drain pipes.
- Gluing and sealing of skirting boards, steps, doorsteps, protective profiles, covers, prefab elements, artificial grass...
- Bonds without primer on almost all materials used in the construction industry, such as aluminium, galvanized and stainless steel, zinc, copper, natural stone, HPL panels, treated wood, gypsum, glass, various synthetic materials, etc. Can also be used on alkali surfaces such as concrete and brick. In this case, a primer is recommended.

| <b>TECHNICAL CHARACTERISTICS</b>                                       |                        |
|--|------------------------|
| Basic ingredient   | MS hybrid polymer      |
| Curing system  | By means of humidity   |
| Number of components   | 1                      |
| Skin formation time (23°C and 50% R.V.)                                | 40 min.                |
| Vulcanisation rate (23°C and 50% R.V.)                                 | 2,5 - 3 mm/24 h        |
| Density: ISO 1183  | 1,48 g/ml              |
| Processing temperature   | +5°C - +40°C           |
| Shelf life, in original packing in dry conditions between +5°C - +25°C | 12 months              |
| Shore A hardness: ISO 868  | 40                     |
| Joint movement capacity: ISO 11600                                     | 25%                    |
| Modulus at 100% elongation: ISO 8339                                   | 0,80 N/mm <sup>2</sup> |
| Elongation at break: ISO 8339  | 230%                   |
| Modulus at break: ISO 8339   | 1,10 N/mm <sup>2</sup> |
| Water vapour permeability: ISO 15106                                   | μ = 6946; sd = 4,9m    |
| Solvent & isocyanate content   | 0%                     |
| Dry matter content   | ca. 100%               |
| Temperature resistance   | -40°C - +90°C          |
| Very good moisture resistance and not sensitive to frost               |                        |

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.

## PACKING AND COLOURS

### 25 cartridges of 290 ml/box - 48 boxes/pallet

**Standard (with SNJF):** White, black, Ral 7004 (signal) grey

**Standard:** Ral 1013 pearl white, Ral 1019 grey beige, Ral 7005 mouse grey, Ral 7023 cement grey, Ral 8007 light brown, Ral 8016 dark brown, Ral 9001 cream, basalte, dark beige, natural stone, terracotta

### 20 sausages of 600 ml/box - 45 boxes/pallet

White, black, grey beige Ral 1019, Ral 7004 (signal) grey, Ral 7005 mouse grey, Ral 7016 anthracite grey, Ral 7023 concrete grey, Ral 7030 stone grey, Ral 7032 pebble grey, Ral 8016 dark (mahogany) brown, Ral 9001 cream, basalte, dark beige, natural stone, terracotta, bronze, middle grey, quartz grey, panel grey, cement grey

Other colours are available on request (75 cartridges or multiples).

## METHOD OF USE

### Preparation

The support must be fixed and rigid enough. The support may be slightly damp. The materials to be joined must be clean and free from dust and grease. If necessary, degrease using **Parasilico Cleaner**, MEK, alcohol, or ethanol. It is advisable to do bonding tests. It is the user's responsibility to check whether the product is suitable for his application. Our technical department could be consulted.

### Primers

For strongly absorbent supports it is recommended to use **DL 2001 Primer**. With double glazing, it is advisable to apply **black DL 2001 primer**. This prevents the contact surface between the glass and sealant from being exposed to UV-radiation.

### Application

- Use in well-ventilated rooms. Good ventilation is important during application and vulcanisation of the product.
- As adhesive: Apply **Parabond Construction** with the supplied nozzle in strips or dots to the base or on the element to be bonded. The strips must be applied in vertical rows. Apply the strips parallel to each other, to allow the humidity to reach the adhesive between the strips. Bring together the parts to be joined as quickly as possible, at least within 10 minutes (this depends on the temperature and relative humidity level). The parts can at this stage still be adjusted. Finally, push down one over the other well or tap with a rubber hammer. It is advised to have a gap of 3.2 mm between the parts to be bonded (spacer blocks or pieces of foam tape may be used), to allow the adhesive to smooth out any distortions (especially important in exterior use or under humid conditions). If the adhesive layer does not have to take up any, or only has to take up a slight mutual distortion between the joining parts, a thinner adhesive layer (at least 1.5 mm) will suffice (for example in interior applications).
- As sealant: Provide shallow joints (on the floor) with a self-adhesive tape or foam tape to prevent triple-sided bonding. The adhesive depth of the movable joint should amount to approx. 2/3 of the joint width. Joints that are too deep should be filled with suitable filler foam (PE or PU-filler foam). With deep floor joints, it is advisable to use a strong PU-filler foam as back-up material. With floor joints, that are subjected to high mechanical load, the sealant should be applied deep. It is better to apply the sealant at an angle sloping from the floor surface to the adhesive surface (rim sides). The sealant should only bond at the sides of the joint.

### Joint dimensions

The necessary width of a dilation joint depends on the temperature fluctuation, properties of the material and the dimensions of the construction elements. Apply at least a joint width of 6 mm.

| Joint width | Joint depth | Allowed difference |
|-------------|-------------|--------------------|
| 6 mm        | 6 mm        | ± 1 mm             |
| 8 mm        | 8 mm        | ± 1 mm             |
| 10 mm       | 6-8 mm      | ± 2 mm             |
| 15 mm       | 10 mm       | ± 2 mm             |
| 20 mm       | 10-12 mm    | ± 2 mm             |
| 25 mm       | 15 mm       | ± 3 mm             |
| 35 mm       | 20 mm       | ± 3 mm             |
| 50 mm       | 30 mm       | ± 3 mm             |

### Tooling

If desired, smooth surface before skin formation with the tooling agent **DL 100** and a scraper.

### Cleaning

Any adhesive that may protrude along the edges can be removed using a stopping knife. Adhesive residue that has not yet dried, can be removed using **Parasilico Cleaner**. Cured adhesive must be removed mechanically.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.

## Painting

Paintable with most water and solvent based paints. Can be painted wet on wet. After 48 hours, the surface must be cleaned first before it can be painted. Pre-testing is necessary. Alkyd paints require an extended drying time.

## SAFETY

Please refer to the safety data sheet.

## LIMITATIONS

- Permanent exposure to high relative humidity may cause fungal growth.
- Not suitable for joints with a width or depth < 5 mm.
- No adhesion on PE, PP, PA, PTFE (Teflon®) and bituminous substrates.
- On bituminous surfaces: use **Paraphalt**.
- On polycarbonate and polyacrylate: use **Parasilico PL**.
- Not compatible with the edge seals of insulating glazing and the PVB films of safety glass. Avoid direct contact.

## TECHNICAL APPROVALS

SNJF (Société National du Joint Français): FACADE n° 3749

Mastic type élastomère classe 25E

ATG (Belgian technical approval) ATG 12/2643

Leeds certificate for low VOC (tested by Eurofins)

FDA approved (Ianesco report Nr 15/19449)

CE

EC1<sup>PLUS</sup>



|  |
|--|
| CE   |
| 14<br>DL Chemicals   |
| EN 15651-1<br>F EXT - INT<br>EN 15651-4<br>PW EXT - INT<br>No. DoP:<br>MP0070001 |



\* Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).



This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.